

Cu Zn5

Common names: 95/5 Brass
95/5 Gilding Metal

A copper-zinc alloy with an alpha phase structure. The alloy has excellent cold-working properties and is generally not susceptible to dezincification and stress corrosion. It is widely used for small-arms ammunition and, due to its attractive golden colour, for decorative applications.

COMPOSITION (weight %)

Cu	94.0-96.0
Zn	rem.

1 SOME TYPICAL USES**Coinage**

Coins, medals and tokens.

Decorative

Emblems, costume jewellery, plaques; good base material for gold plate and vitreous enamel.

Munitions

Small arms ammunition including bullet envelopes (clad on steel), fuse caps and primer caps.

2 PHYSICAL PROPERTIES

	Metric Units	English Units
2.1 Density at 20 °C 68 °F	8.85 g/cm ³	0.320 lb/in ³
2.2 Melting range	1 055-1 070 °C	1 930-1 960 °F
2.3 Coefficient of thermal expansion (linear) at:		
20 to 100 °C 68 to 212 °F	0.000 017 per °C	0.000 010 per °F
20 to 300 °C 68 to 572 °F	0.000 018 " "	0.000 010 " "
2.4 Specific heat (thermal capacity) at:		
20 °C 68 °F	0.09 cal/g °C	0.09 Btu/lb °F
2.5 Thermal conductivity at:		
-200 °C -328 °F	0.31 cal cm/cm ² s °C	74 Btu ft/ft ² h °F
20 °C 68 °F	0.56 " "	135 " "
200 °C 392 °F	0.65 " "	157 " "
2.6 Electrical conductivity (volume) at:		
-196 °C -321 °F (annealed)	71 m/ohm mm ²	123 % IACS
20 °C 68 °F (")	32 " "	56 " "
200 °C 392 °F (")	23 " "	40 " "
-196 °C -321 °F (fully cold worked)	67 " "	115 " "
20 °C 68 °F (" " ")	31 " "	53 " "

continued overleaf

INDEX NUMBERS RELATE TO LITERATURE REFERENCES (see page 8); INDEX LETTERS RELATE TO FOOTNOTES AT END OF TABLE

Prepared by
CONSEIL INTERNATIONAL POUR LE
DEVELOPPEMENT DU CUIVRE (CIDEC)
100, rue du Rhône - 1204 GENEVE

Distributed by
Centre d'Information Cuivre, Laitons, Alliage
67 Bld. Berthier - 75 Paris XVIIe

DATA SHEET No. D1
Cu Zn5
© 1970 Edition

2 PHYSICAL PROPERTIES (continued)

		Metric Units	English Units
2.7 Electrical resistivity (volume) at:	−196 °C −321 °F (annealed)	0.014 ohm mm ² /m 1.4 microhm cm	8.4 ohms (circ mil/ft) 0.55 microhm in
	20 °C 68 °F („)	0.031 ohm mm ² /m 3.1 microhm cm	19 ohms (circ mil/ft) 1.2 microhm in
	200 °C 392 °F („)	0.043 ohm mm ² /m 4.3 microhm cm	26 ohms (circ mil/ft) 1.7 microhm in
	−196 °C −321 °F (fully cold worked)	0.015 ohm mm ² /m 1.5 microhm cm	9.0 ohms (circ mil/ft) 0.59 microhm in
	20 °C 68 °F („ „ „)	0.032 ohm mm ² /m 3.2 microhm cm	20 ohms (circ mil/ft) 1.3 microhm in
	2.8 Temperature coefficient of electrical resistance at:	20 °C 68 °F (annealed) applicable over range from 0 to 100 °C 32 to 212 °F	0.002 3 per °C (56% IACS)
20 °C 68 °F (fully cold worked) applicable over range from 0 to 100 °C 32 to 212 °F		0.002 2 „ „ (53% IACS)	0.001 2 „ „ (53% IACS)
2.9 Modulus of elasticity (tension) at 20 °C 68 °F:	annealed	13 000 kg/mm ²	18 500 000 lb/in ²
	cold worked	12 300–13 000 kg/mm ²	17 500 000–18 500 000 lb/in ²
2.10 Modulus of rigidity (torsion) at 20 °C 68 °F:	annealed	4 750 kg/mm ²	6 750 000 lb/in ²
	cold worked	4 500–4 750 kg/mm ²	6 400 000–6 750 000 lb/in ²

N.B.: The values shown in Section 2, which have been appropriately rounded in view of the composition range involved, are based on selected literature references.

3 FABRICATION PROPERTIES

The information given in this table is for general guidance only, since many factors influence fabrication techniques.

The values shown are approximate only, since those used in practice are dependent upon form and size of metal, equipment available, techniques adopted and properties required in the material.

	Metric Units	English Units
3.1 Casting temperature range	1 140–1 200 °C	2 085–2 190 °F
3.2 Annealing temperature range	425– 600 °C	795–1 110 °F
Stress relieving temperature range	200– 300 °C	390– 570 °F
3.3 Hot working temperature range	750– 900 °C	1 380–1 650 °F
3.4 Hot formability		Good
3.5 Cold formability		Excellent
3.6 Cold reduction between anneals		90% max.
3.7 Machinability:		See General Data Sheet No. 2
Machinability rating (free-cutting brass = 100)		25
3.8 Joining methods:		See General Data Sheet No. 3.4
Soldering		Excellent
Brazing		Excellent
Oxy-acetylene welding		Good
Carbon-arc welding		Not recommended
Gas-shielded arc welding		Good
Coated metal-arc welding		Not recommended
Resistance welding: spot and seam		Not recommended
butt		Good

4 NATIONAL SPECIFICATIONS FOR MANUFACTURED FORMS

and ISO Recommendation

Country	Designation of Standards	Designation of Material in Standards	Specification for Chemical Composition ^(a)	Plate Sheet Strip	Rod	Wire	Tube	Sections	Forgings
								Shapes	
Australia . . .	SAA	—	—	—	—	—	—	—	—
Belgium . . .	NBN	—	—	—	—	—	—	—	—
Canada . . .	CSA	HC.Z5 (or 210)	—	HC.4.2	—	HC.5.21	—	—	—
Chile . . .	INDITECNOR	Cu Zn5	247 n./68	—	—	—	—	—	—
France . . .	NF	—	—	—	—	—	—	—	—
Germany . . .	DIN	Cu Zn5 (2.0020)	17 660	17 670	17 672	17 672	17 671	—	—
India . . .	IS	—	—	3167	—	—	—	—	—
Italy . . .	UNI	—	—	—	—	—	—	—	—
Japan . . .	JIS	RBsP1 RBsR1 RBsW1	—	H 3241 H 3331	—	H 3551	—	—	—
Netherlands	N or NEN ^(b)	—	—	—	—	—	—	—	—
South Africa	SABS	—	—	—	—	—	—	—	—
Spain . . .	UNE	—	—	—	—	—	—	—	—
Sweden . . .	SIS	—	—	—	—	—	—	—	—
Switzerland . . .	VSM	—	—	—	—	—	—	—	—
United Kingdom . . .	BS	CZ125	—	2870 STA 17	—	—	—	—	—
United States ^(c)	ASTM	No. 210	—	B 36 B 134	—	B 134	—	—	—
International Organization for Standardization	ISO	—	—	—	—	—	—	—	—

^(a) Applicable when the chemical composition is not given in the specifications for wrought forms.

^(b) Older specifications bear prefix N; for new specifications the NEN prefix is used.

^(c) In the United States, bar and flat wire are covered under the Plate-Sheet-Strip column.

5 MECHANICAL PROPERTIES

5.1 Mechanical properties at room temperature

Tensile properties	see tables 5.1.1/2/3
Hardness	“ “ 5.1.1/2/3
Shear strength	“ “ 5.1.1/2/3
Modulus of elasticity (tension)	see 2.9
Modulus of rigidity (torsion)	see 2.10

5.2 Mechanical properties at low temperature

Tensile properties	see table 5.2.1
Impact properties	“ “ 5.2.1

5.3 Mechanical properties at elevated temperature

Short-time tensile properties	see table 5.3.1
Creep properties	see tables 5.3.2.1/2

5.4 Fatigue properties

Fatigue strength at room temperature	see table 5.4.1
--------------------------------------	-----------------

5.1 MECHANICAL PROPERTIES AT ROOM TEMPERATURE^(a)

5.1.1 Typical Tensile Properties and Hardness Values—Metric Units

This table is representative of practice in many European countries. For British and American practices, see tables 5.1.2 and 5.1.3, respectively.

The values shown represent reasonable approximations for general engineering use, taking account of variations in composition and manufacturing procedures. For design purposes, national specifications should be consulted.

For a given temper, individual elongation values may show some variation above or below the typical values indicated.

Form	Temper	Tensile Strength kg/mm ²	Proof Stress 0.2% offset kg/mm ²	Elongation		Hardness		Shear Strength kg/mm ²	Typical Size Related to Properties Shown ^(b)
				%	gauge length	Brinell	Vickers		
Plate Sheet Strip	Annealed (grain size 0.015 mm)	27	10	45	50 mm	65	68	20	0.2–1.5 mm thick
	Typical Cold Worked Tempers	34	24	20	50 mm	85	89	24	0.2–3 mm thick
		39	32	8	50 mm	105	110	25	0.2–2 mm thick
43		38	4	50 mm	120	125	26	0.2–1.5 mm thick	
Wire	Annealed	27	—	33	100 mm	—	—	20	1.5–6 mm diam.
		30	—	30	100 mm	—	—	23	0.2–1.5 mm diam.
	Typical Cold Drawn Tempers	45	—	3	100 mm	—	—	26	0.2–1.5 mm diam.
		55	—	—	—	—	—	28	„

^(a) It will be noted that tables 5.1.1, 5.1.2 and 5.1.3, giving typical tensile properties and hardness values in Metric, English and American units, respectively, are not directly comparable. This is because the properties quoted reflect to some extent the metalworking techniques, specification practices, and testing procedures in the countries concerned, and in view of the different sizes of products referred to in these tables. Individual manufacturers of semi-fabricated products can, however, normally meet the requirements of any national standard.

^(b) It is possible to obtain sizes outside the ranges given in this column, but information on their mechanical properties should be obtained from the metal manufacturers.

5.1.2 Typical Tensile Properties and Hardness Values—English Units

This table is based on British practice. For other European and American practices, see tables 5.1.1 and 5.1.3, respectively.

The values shown represent reasonable approximations for general engineering use, taking account of variations in composition and manufacturing procedures. For design purposes, national specifications should be consulted.

For a given temper, individual elongation values may show some variation above or below the typical values indicated.

Form	Temper ^(a)	Tensile Strength ton/in ²	Proof Stress 0.1% offset ton/in ²	Elongation		Vickers Hardness	Shear Strength ton/in ²	Typical Size Related to Properties Shown ^(b)
				%	gauge length			
Sheet Strip	Annealed							
	grain size 0.025 mm	16	4	55	2 in.	55	11	0.01–0.125 in. thick
	grain size 0.015 mm	17	5	52	2 in.	70	12	„
	Cold Worked							
	Quarter Hard	17	9	45	2 in.	85	12	0.01–0.375 in. thick
	Half Hard	19	13	35	2 in.	100	13	0.01–0.25 in. thick
	Hard	23	19	13	2 in.	120	15	0.01–0.1 in. thick
	Extra Hard	27	23	8	2 in.	130	16	„

^(a) The recognised temper designations used in the relevant or nearest British Standards are also given, to clarify the cold-worked tempers shown.

^(b) It is possible to obtain sizes outside the ranges given in this column, but information on their mechanical properties should be obtained from the metal manufacturers.

5.1.3 Typical Tensile Properties and Hardness Values—American Units

This table is based on American practice and the temper designations shown are those referred to in ASTM and other American Standards. For British and other European countries' practices, see tables 5.1.2 and 5.1.1, respectively.

The values shown represent reasonable approximations for general engineering use, taking account of variations in composition and manufacturing procedures. For design purposes, national specifications should be consulted.

For a given temper, individual elongation values may show some variation above or below the typical values indicated.

Form	Temper	Tensile Strength psi	Yield Strength 0.5% extension under load psi	Elongation		Rockwell Hardness			Shear Strength psi	Typical Size Related to Properties Shown ^(a)
				%	gauge length	F	B	30 T		
Flat Products (Plate, Sheet, Strip, Bar and Flat Wire)	Annealed									
	grain size 0.050 mm	34 000	10 000	45	2 in.	46	—	—	28 000	0.040 in. thick
	grain size 0.035 mm	35 000	11 000	45	2 in.	52	—	4	28 000	"
	grain size 0.015 mm	38 000	14 000	42	2 in.	60	—	15	30 000	"
	Cold Worked									
	Quarter Hard	42 000	32 000	25	2 in.	—	38	44	32 000	0.040 in. thick
	Half Hard	48 000	40 000	12	2 in.	—	52	54	34 000	"
	Hard	56 000	50 000	5	2 in.	100	64	60	37 000	"
	Extra Hard	61 000	55 000	4	2 in.	—	70	64	39 000	"
	Spring	64 000	58 000	4	2 in.	—	73	66	40 000	"
Rod	Annealed	37 000	13 000	50	2 in.	50	—	—	29 000	0.50 in. diam.
	Cold Worked Eighth Hard	42 000	32 000	25	2 in.	—	38	44	32 000	0.50 in. diam.
Wire	Annealed									
	grain size 0.035 mm	37 000	—	50	2 in.	—	—	—	29 000	0.080 in. diam.
	grain size 0.015 mm	39 000	—	48	2 in.	—	—	—	31 000	"
	Cold Worked									
	Eighth Hard	41 000	—	27	2 in.	—	—	—	32 000	0.080 in. diam.
	Quarter Hard	47 000	—	13	2 in.	—	—	—	34 000	"
	Half Hard	57 000	—	6	2 in.	—	—	—	38 000	"
	Hard	71 000	—	4	2 in.	—	—	—	40 000	"
Extra Hard	80 000	—	3	2 in.	—	—	—	45 000	"	
Spring	87 000	—	3	2 in.	—	—	—	48 000	"	

^(a) It is possible to obtain sizes different from those given in this column, but information on their mechanical properties should be obtained from the metal manufacturers.

5.2 MECHANICAL PROPERTIES AT LOW TEMPERATURE

5.2.1 Tensile Properties

Form	Temper	Testing Temperature		Tensile Strength			Proof Stress 0.2% offset kg/mm ²
		°C	°F	kg/mm ²	ton/in ²	psi	
Rod ^{(1)(a)}	Annealed (grain size 0.023 mm)	-195	-319	38	24	54 000	9.60 ^(b)

(a) These values were determined on material just outside the composition range of the alloy and are presented for guidance only, since no other information is available.

(b) This value was originally reported in psi; in this table it is given in kg/mm² to 3 significant figures.

N.B.:—Original values are printed in **bold type**; other values are converted.

—Data not available:

Proof stress, 0.1% offset
Yield strength, 0.5% extension under load
Elongation
Reduction of area
Impact strength.

5.3 MECHANICAL PROPERTIES AT ELEVATED TEMPERATURE

5.3.1 Short-Time Tensile Properties

Form	Temper	Testing Temperature		Tensile Strength			Proof Stress		Elongation % on $5.65 \sqrt{S_0}$
		°C	°F	kg/mm ²	ton/in ²	psi	0.2% offset kg/mm ²	0.1% offset ton/in ²	
Rod ^{(2)(a)} 10.5 mm diam. 0.41 in. diam.	Cold Worked 51%	20	68	37.0	23.5	52 500	35.4	20.3^(b)	19.2
		200	392	31.6	20	45 000	30.0	17.1^(b)	17.4
		300	572	27.3	17.5	39 000	25.0	14.6^(b)	13.0
Rod ⁽³⁾ 12.7 mm diam. 0.5 in. diam.	Annealed	25	77	23.5	15	33 500	4.85^(c)	—	—
		300	572	16.5	10.5	23 500	3.71^(c)	—	—
		500	932	9.5	6	13 380	3.16^(c)	—	—

(a) These values were determined on material just outside the composition range of the alloy and are presented for guidance only, since no other information is available.

(b) This value was originally reported in kg/mm²; in this table it is given in ton/in² to 3 significant figures.

(c) This value was originally reported in psi; in this table it is given in kg/mm² to 3 significant figures.

N.B.:—Original values are printed in **bold type**; other values are converted.

—The 0.5% extension under load yield strength values are not available.

5.3.2 Creep Properties

5.3.2.1 Original Creep Data

Form	Temper	Testing Temperature		Stress			Duration h	Total Extension % ^(a)
		°C	°F	kg/mm ²	ton/in ²	psi		
Rod^{(2) (b)} 10.5 mm diam. 0.41 in. diam.	Cold Worked 51%	200	392	10.0	6.3	14 200	3 305	0.123
				12.0	7.6	17 100	1 995	0.21
				14.0	8.9	19 900	1 989	0.38
				14.3	9.1	20 300	2 011	0.51

(a) Total creep; does not include the initial elastic extension.

(b) These values were determined on material just outside the composition range of the alloy and are presented for guidance only, since no other information is available.

N.B.:—Original values are printed in **bold type**; other values are converted.

—Data not available:

Intercept,

Minimum creep rate.

5.3.2.2 Stress for Designated Extension

Form	Temper	Testing Temperature		Stress for Designated Extension											
		°C	°F	0.1% in 1 000 h			0.2% in 1 000 h			0.1% in 2 000 h			0.2% in 2 000 h		
				kg/mm ²	ton/in ²	psi	kg/mm ²	ton/in ²	psi	kg/mm ²	ton/in ²	psi	kg/mm ²	ton/in ²	psi
Rod^{(2) (a)} 10.5 mm diam. 0.41 in. diam.	Cold Worked 51%	200	392	10.0	6.3	14 200	12.8	8.1	18 200	9.3	5.9	13 200	11.9	7.5	16 900

(a) These values were determined on material just outside the composition range of the alloy and are presented for guidance only, since no other information is available.

N.B.: Original values are printed in **bold type**; other values are converted.

5.4 FATIGUE PROPERTIES

5.4.1 Fatigue Strength at Room Temperature

Data has recently been published in the following paper:

■ France, W.D., Trout, D.E. and Mulholland, J.A. Fatigue Characteristics of Five Copper-Base Strip Alloys Commonly Used for Spring Applications. J. Materials, Vol. 4 (1969), No. 3, Sept., pp. 633-646.

REFERENCES

MECHANICAL PROPERTIES (SECTION 5)

(1) Roberson, J.A. and Grosskreutz, J.C. Fatigue of Copper-Zinc Alloys at 100 K. Acta Metall., Vol. 11 (1963) July, pp. 795-798.

(2) Dies, K. and Jung-König, W. Zeitstandverhalten einiger technischer Kupferlegierungen in der Wärme. Metall, Vol. 16 (1962) No. 11, pp. 1097-1102.

(3) Crowe, C.H. Properties of Some Copper Alloys at Elevated Temperatures. ASTM Bull. No. 250, (1960) Dec., pp. 30-31.